

INVERNESS
P2IS



TURNBERRY
P2TY



WINDSOR
P2WR



INVERNESS
P2IS



RHODES
P2RS




ASCOT
P2AT



CAMBRIDGE
P2CE

■ Specification Information

Description	Pi
Grade	2
Content	100% Recycled Polyester
Repeat	10.5" Vertical, 7.2" Horizontal
Width	66"
Weight	10.8 +/- 1 oz./Linear Yard
Fabric Treatment	None
Performance	
 Abrasion	Decorative with full serviceability. (# 10 Cotton Duck) ASTM D-4157 Mod.: 15,000 Double Rubs. Abrasion resistance is the surface wear of a fabric caused by rubbing and contact with another fabric.
 Physical Properties	Passes Breaking Strength (ASTM D-5034): 243 lbs. Warp, 166 lbs. Fill. Breaking strength is the measurement of stress exerted to pull a fabric apart under tension.
 Colorfastness to Wet and Dry Crocking	Passes (AATCC 8): Dry Crocking, Class 4. Wet Crocking, Class 4. Crocking is the transfer of dye from the surface of a dyed or printed fabric onto another surface by rubbing.
 Colorfastness to Light	Passes (AATCC-16 – 40 hrs.): L5. Colorfastness to light refers to a material's degree of resistance to the fading effect of light.
 Flame Resistance	Passes California Technical Bulletin # 117 Section E – Class I. Flame resistance is the measurement of a fabric's performance when it is exposed to specific sources of ignition.

Colors may vary slightly between dye lots.

KI is a registered trademark of
Krueger International, Inc.

© 2008 KI Litho in USA KI-32446/HC/EWB/408

