




RATTAN
H1RN




COCONUT SHELL
H1CL



RATTAN
H1RN




CHAMOMILE
H1CE



CATERPILLAR
H1CR






PAPER MONEY
H1PY



KNIGHT
H1KT

■ Specification Information

Description	Hypothesis
Grade	1
Content	100% Recycled Polyester
Repeat	27" Vertical, 27" Horizontal
Width	66"
Weight	7.6 oz./Linear Yard
Fabric Treatment	Acrylic
Performance	
 Physical Properties	Passes Breaking Strength ASTM D1682-64: 74.3 lbs. Warp, 76.4 lbs. Fill. Breaking strength is the measurement of stress exerted to pull a fabric apart under tension. Passes Seam Slippage ASTM D3597-D434-75: 33.9 lbs. Warp, 56.5 lbs. Fill. Seam slippage is the movement of yarns in a fabric that occurs when it is pulled apart at a seam.
 Colorfastness to Wet and Dry Crocking	Passes AATCC 8-1981 Dry Crocking, Class 5. Wet Crocking, Class 5. Crocking is the transfer of dye from the surface of a dyed or printed fabric onto another surface by rubbing.
 Colorfastness to Light	Passes AATCC-46A-1974 or AATCC 16-E1976: Class 4/40 hrs. min. Colorfastness to light refers to a material's degree of resistance to the fading effect of light.
 Flame Resistance	Passes California Technical Bulletin #117 Section E – Class 1. Flame resistance is the measurement of a fabric's performance when it is exposed to specific sources of ignition.

Colors may vary slightly between dye lots.

KI is a registered trademark of
Krueger International, Inc.

© 2008 KI Litho in USA KI-32440/HC/EWB/408

