

■ **Naturalize Grade 1**

Vertical Fabric



MAIZE
N1641



BUTTERSCOTCH
N1642



STONE
N1638



GRANITE
N1644



MAIZE
N1641



GRAVEL
N1640



EUCALYPTUS
N1649



CELERY
N1647



GREEN TEA
N1648



SLATE BLUE
N1645

■ Specification Information

Description	Naturalize
Grade	1
Content	100% Polyester
Repeat	None
Width	66"
Weight	12.5 oz./Linear Yard +/-0.5
Fabric Treatment	None
Performance	
 Abrasion	30,000 double rubs. Abrasion resistance is the surface wear of a fabric caused by rubbing and contact with another fabric.
 Physical Properties	Passes Breaking Strength ASTM D5034-95: 186 lb. Warp, 164 lbs. Fill. Breaking strength is the measurement of stress exerted to pull a fabric apart under tension.
 Colorfastness to Wet and Dry Crocking	Passes AATCC 8-2001 Dry Crocking, Class 5.0. Wet Crocking, Class 5.0. Crocking is the transfer of dye from the surface of a dyed or printed fabric onto another surface by rubbing.
 Colorfastness to Light	Passes AATCC 16: Class 4-5 at 40 hrs. minimum. Colorfastness to light refers to a material's degree of resistance to the fading effect of light.
 Flame Resistance	Passes ASTM E 84 (Tunnel Test): Passes (Class A or I). Flame resistance is the measurement of a fabric's performance when it is exposed to specific sources of ignition.

Colors may vary slightly between dye lots.

KI is a registered trademark of
Krueger International, Inc.

© 2008 KI Litho in USA KI-32391/HC/EWB/408

